

PRODUCT DETAILS

Thickness (mm)	6, 8, 12, 15, 18, 19
Size (feet)	8 x 4

TEST REPORT

Parameters	Test Method	Units	Test Result
Density	IS : 2380 (P-III)	gm/cm3	0.65
Hardness	ASTM D 2240	Shore D	87
Tensile Strength	IS : 2380 (P-VI)	Mpa	4.56
Elongation at Break		%	6.49%
Screw Withdrawal Test - Face	IS : 2380 (P-XIV)	N	1487.68
Izod Impact Strength Test	ASTM D 256	J/m	10.46
Charpy Impact Strength Test	ASTM D 6110	J/m	10.27
Heat Depression Temperature	ASTM D 648	0 C	68.4
Modulus of Rupture [MOR]	IS : 2380 (P-IV)	Mpa	10.54
Modulus of Elasticity [MOE]		Mpa	1301
Water Absorption Test (after 2 Hrs.)	IS : 2380 (P-XVI)	%	0.26%
Water Absorption Test (after 24 Hrs.)		%	0.71%

Other ranges:



CENTURYCOMPOSITES

WPC | PVC

BOARDS | DOORS | DOOR FRAMES | LOUVERS

+913339403950 1800-5722-122

Address:

Century Plyboards (India) Limited
1006/1009, Sakar III, 10th Floor, Income Tax Circle, Ahmedabad, Gujarat 380014

Follow us on:    


CENTURYCOMPOSITES
— CENWOOD BOARDS —



ENGINEERED
for
DURABILITY & STRENGTH



What is Cenwood?

Cenwood Board is a premium, high-density surface board, built for **unmatched strength, durability, and convenience**. **100% waterproof** and **termite-proof**, it withstands all weather conditions and resists wear for years. Its ready-to-use surface needs no extra sanding, making it ideal for lamination and decorative finishes in cabinetry, furniture, wall cladding, and partitions.



Why Cenwood?

**Higher
Screw Holding Capacity.
Higher Reliability.**



Graded
Density



100%
Recyclable



100% Termite
and Borer Proof



Design
Flexibility



Lead-Free







**Works like wood,
looks like wood but
better and durable
than wood**

- Modular Kitchen
- Wardrobe
- Bathroom Vanity
- Cabinets



CENTURYCOMPOSITES
— CENWOOD BOARDS —

*Engineered for
durability and
strength.*



- Wall Panelling
- Decking
- Storage Units
- Fencing